# **Technical Data**



# TUFCUT AQUA WATER SOLUBLE SEMI-SYNTHETIC CUTTING FLUID



**TUFCUT AQUA** is a semi synthetic cutting fluid for cutting operations on all types of metal parts (steel, copper, aluminium, stainless steel, etc...).

Tufcut Aqua significantly extends the life time of the cutting tool and gives a superb anti-corrosion coating the machined parts. Cuttings and swarf are easily removed.

Tufcut Aqua remains usable considerably longer than traditional fluids due to specifically developed active lubricating components

- Rapid removal of cuttings, maintaining a clean lubricating fluid and allowing increased cutting speeds.
- Transparent solution allows a clear view of the machining operation.
- The cutting fluid contains excellent surfactants, helping to maintain tool cleanliness.
- Easy to clean at low temperatures with Ambersil Aquasafe.
- Does not contain nitrites or heavy metals.

### **APPLICATIONS**

Suitable for a wide range of cutting operations (see table below).

# **DIRECTIONS**

To set up a cutting fluid reservoir, add Tufcut Aqua to water at the percentages indicated in the following table:

|                            | Metals to be machined |           |           |        |                 |  |  |  |  |
|----------------------------|-----------------------|-----------|-----------|--------|-----------------|--|--|--|--|
| Cutting operation          | Steel                 | Cast Iron | Aluminium | Bronze | Stainless Steel |  |  |  |  |
| Boring out                 | 4-6%                  | 4-6%      | 5-7%      | 4-6%   | 5-7%            |  |  |  |  |
| Drifting                   | 6-10%                 | 6-8%      | 6-10%     | 6-10%  | 6-10%           |  |  |  |  |
| Thread cutting with chisel | 4-6%                  | 4-6%      | 5-7%      | 4-6 %  | 5-7%            |  |  |  |  |
| Drilling                   | 6-10%                 | 6-8%      | 6-10%     | 6-10%  | 6-10%           |  |  |  |  |
| Milling                    | 4-6%                  | 3-5%      | 4-6%      | 3-5%   | 4-6%            |  |  |  |  |
| Mortising                  | 6-10%                 | 6-8%      | 6-10%     | 6-10%  | 6-10%           |  |  |  |  |
| Piercing                   | 4-6%                  | 4-6%      | 5-7%      | 4-6%   | 5-7%            |  |  |  |  |
| Planing                    | 4-6%                  | 4-6%      | 5-7%      | 4-6%   | 4-6%            |  |  |  |  |
| Grinding                   | 2-3%                  | 2-3%      | 2-3%      | 2-3%   | 2-3%            |  |  |  |  |
| Sawing                     | 4-6%                  | 4-6%      | 5-7%      | 5-7%   | 4-6%            |  |  |  |  |
| Edge cutting with moulds   | 4-6%                  | 4-6%      | 5-7%      | 4-6%   | 5-7%            |  |  |  |  |
| Edge cutting with chisel   | 6-10%                 | 6-8%      | 6-10%     | 6-10%  | 6-10%           |  |  |  |  |
| Thread cutting             | 6-10%                 | 6-8%      | 6-10%     | 6-10%  | 6-10%           |  |  |  |  |
| Turning                    | 4-6%                  | 3-5%      | 4-6%      | 3-5%   | 4-6%            |  |  |  |  |
| Cutting of cylinders       | 4-6%                  | 4-6%      | 4-6%      | 4-6%   | 4-6%            |  |  |  |  |

The concentration of the cutting fluid can be controlled by measuring the refractive index on a daily basis and comparing with the following table:

| Refractometer display | 1.5 | 2.2 | 3.0 | 3.7 | 4.4 | 5.2 | 5.9 | 6.7 | 7.4 |
|-----------------------|-----|-----|-----|-----|-----|-----|-----|-----|-----|
| Concentration in %    | 2   | 3   | 4   | 5   | 6   | 7   | 8   | 9   | 10  |

Check the pH of the fluid at weekly intervals, check for bacterial growth on a monthly basis.

#### **TECHNICAL DATA**

Appearance : Clear amber liquid

Density : 1.1

Flash Point : Non-Flammable

pH of Concentrate : 9.5 pH of a 5% Solution : 9

 Viscosity @ 20 °C
 : 32.6 mm²/s

 @ 40 °C
 : 13.3 mm²/s

 Saponification Factor
 : 65 mg KOH/g

Extreme Pressure Property : with charge: 80 daN - imprint: 0.6 mm

Packaging : 2 x 5Ltr, 1 x 25Ltr

#### **STORAGE**

The product may be stored at normal ambient temperatures and has a shelf life of not less than 36 months with correct storage.

#### **HEALTH AND SAFETY**

Health and Safety sheet available separately.

# **TECHNICAL SERVICE**

CRC Industries UK Ltd provides a technical support service and maintains a constant programme of research and development. We are able to assist customers with specific product enquiries and requests for technical information.

# **MISREPRESENTATION ACT 1967**

# **TRADE DESCRIPTIONS ACT 1968**

The information given in this publication is based on our experience and reports from customers. There are many factors outside our control and knowledge which affect the use and performance of our products and for which reason no warranty is given, express or implied. Users should make their own tests to determine the applicability of such information or the suitability of any products for their own particular purposes. Statements concerning the use of the products described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is to be assumed.

CRC Industries UK Ltd, Ambersil House, Wylds Road, Bridgwater, Somerset, TA6 4DD

Tel: +44 (0) 1278 727200 Fax: +44 (0) 1278 425644

Web: www.ambersil.com E-mail: sales.uk@crcind.com

Created: June 2009